Research Repository UCD

Title	Generalized model of photopolymer behavior for use in optimized holographic data storage scheduling algorithms
Authors(s)	Kelly, John V., Gleeson, M. R., Close, Ciara E., O'Neill, Feidhlim T., Sheridan, John T.
Publication date	2006-10-10
Publication information	Kelly, John V., M. R. Gleeson, Ciara E. Close, Feidhlim T. O'Neill, and John T. Sheridan. "Generalized Model of Photopolymer Behavior for Use in Optimized Holographic Data Storage Scheduling Algorithms." Optical Society of America, 2006.
Conference details	OLED Circuits, Solar Cells and Organic Memory (OPTuC) at Organic Photonics and Electronics (OPE) Rochester, New York, October 10, 2006
Publisher	Optical Society of America
Item record/more information	http://hdl.handle.net/10197/3664
Publisher's statement	This paper was published in Frontiers in Optics and is made available as an electronic reprint with the permission of OSA. The paper can be found at the following URL on the OSA website: http://www.opticsinfobase.org/abstract.cfm?uri=OPE-2006-OPTuC5 . Systematic or multiple reproduction or distribution to multiple locations via electronic or other means is prohibited and is subject to penalties under law.

Downloaded 2023-04-07T10:52:29Z

The UCD community has made this article openly available. Please share how this access benefits you. Your story matters! (@ucd_oa)

© Some rights reserved. For more information

Generalized Model of Photopolymer Behavior for Use in Optimized Holographic Data Storage Scheduling Algorithms

John V. Kelly, Michael R. Gleeson, Ciara E. Close,
Feidhlim T. O' Neill, John T. Sheridan^{a)}

UCD School of Electrical, Electronic and Mechanical Engineering, University College Dublin, Belfield, Dublin 4, Ireland.
email: john.sheridan@ucd.ie

Abstract: A generalized model of photo-polymerization in free radical chainforming polymers has been developed. Applying this model to data storage, optimized scheduling algorithms are developed for the multiplexing of multiple data pages of uniform diffraction efficiency.

© 2006 Optical Society of America

OCIS codes: (050.7330) Volume holographic gratings; (090.2900) Holographic recording materials; (090.2890) Holographic optical elements.

1. Introduction

With current technologies reaching the limit of their storage capabilities the optical data industry is searching for the next generation of storage system to meet the demands of the digital age. One possible solution is the use of holographic techniques where terabit capacity has been predicted and photopolymers are proving to be the recording medium of choice.

The generalized nonlocal polymerization driven diffusion model (NPDD) is used to describe holographic grating formation in free radical chain forming polymers and can be described using the following equation.

$$\frac{\partial u(x,t)}{\partial t} = D \left[H(x,t) \frac{\partial^2 u(x,t)}{\partial x^2} - u(x,t) \frac{\partial^2 H(x,t)}{\partial x^2} \right] - \int_{-\infty}^{+\infty} \int_0^t R(x,x';t,t') F(x',t') \times \left[u(x',t') \right]^\beta dt' dx' - \frac{u(x,t)}{u(x,t) + N(x,t)} \frac{\partial H(x,t)}{\partial t} \quad (1)$$

where $u(x, t)$ is the free-monomer concentration, D is the monomer diffusion constant, $F(x, t)$ is the polymerization rate, $N(x, t)$ is the polymer concentration, $R(x, x'; t, t')$ is the nonlocal response function, $H(x, t)$ is the hole concentration, and β is a factor introduced to specify the dominant chain termination mechanism, either bimolecular ($\beta = 1$) or primary ($\beta = 2$). In this paper we examine the bimolecular case, $\beta = 1$. Volume changes are accounted for by assuming the generation of holes or free volume on the conversion of polymer to monomer. These holes can then diffuse and decay leading to volume changes and surface relief patterns in the material.¹

2. Optimized Scheduling

We develop an algorithm based on the NPDD model, which determines an appropriate recording schedule for use in photopolymer materials.² The model is solved using a finite difference technique and an optimized schedule determined. The inverse-square scaling law of holographic diffraction given in Eq. 2 is also examined and shown to hold for photopolymer materials governed by the NPDD model for cases of gratings with weak diffraction efficiency.

$$\eta = \frac{\Gamma}{M^2} \quad (2)$$

η is the diffraction efficiency, Γ is a material constant and M is the number of gratings (pages) stored. However for cases where a small number of high diffraction efficiency gratings the relationship is more complex. We examine this and comparisons to experimental data using the model showing a $\sin^2$ relationship to hold.

¹ J. V. Kelly, F. T. O'Neill, J. T. Sheridan, "Holographic photopolymer materials: non-local polymerisation driven diffusion under non-ideal kinetic conditions," J. Opt. Soc. Am. B **22**, 407-416 (2005).

² J. T. Sheridan, M. R. Gleeson, J. V. Kelly, F. T. O'Neill, "Nonlocal polymerisation driven diffusion model based examination of the scaling law for holographic data storage," Opt. Lett. **30**, No. 3, 239-241, (2005).